

BASIC PROPERTIES				ABS									
				General purpose									
				High impact ← → High stiffness					High flow				
Properties (under ISO 10350)	Standard	Conditions	Units	321	220	121	120	026	190	191	190F	191F	
1. Rheological properties													
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	9	12	14	16	19	23	26	47	38	
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	9	13	14	17	20	24	27	49	40	
2. Mechanical properties													
Tensile stress at yield	ISO527-1	50mm/min	MPa	35	41	46	51	58	53	45	46	42	
Tensile stress at yield	ISO527-1	5mm/min	MPa	—	—	—	—	—	—	—	—	—	—
Flexural modulus	ISO178	2mm/min	MPa	1800	2150	2450	2700	2900	2600	2400	2250	2050	
Flexural strength	ISO178	2mm/min	MPa	56	66	75	82	92	83	73	69	63	
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	36	32	27	17	7	11	22	17	25	
	ISO179	0°C	kJ/m²	—	—	—	—	—	—	—	—	—	
	ISO179	-30°C	kJ/m²	—	—	—	—	—	—	—	—	—	
3. Thermal properties													
Vicat softening temperature	ISO306	Load:50N	°C	94	98	101	103	103	101	100	91	91	
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	76	79	81	83	84	82	80	74	74	
4. Other properties													
Density	ISO1183	23°C	g/cm³	1.02	1.04	1.05	1.05	1.06	1.06	1.05	1.05	1.05	
Rockwell hardness	ISO2039-2	R scale	—	89	103	109	111	116	113	109	—	—	
	ISO2039-2	M scale	—	—	—	—	—	—	—	—	—	—	
5. Properties under other standards													
Rockwell hardness(2.5mm)	ordinal	R scale	—	83	96	103	108	113	108	103	100	95	
Linear expansion coefficient	ASTM D696	—	10⁻⁵/°C	—	—	—	—	—	—	—	—	—	
Mold shrinkage	ASTM D955	—	%	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	
Surface resistance	ASTM D257	—	Ω	—	—	—	—	—	—	—	—	—	
Volume resistance	original	—	Ω · cm	—	—	—	—	—	—	—	—	—	
Thermal conductivity	ASTM D 177	—	W/m·°C	—	—	—	—	—	—	—	—	—	
UL class	UL94	—	—	1.5mm HB	1.5mm HB	1.5mm HB	1.5mm HB	1.5mm HB	1.5mm HB	1.5mm HB	1.5mm HB	1.5mm HB	
Relative temperature index	UL746A	—	°C	60	60	80	60	60	60	60	60	60	
Ball pressure temperature (Registered number)	EMAC	—	°C	—	90	90	90	90	85	85	85	85	
				(B-1558)	(B-1558)	(B-1558)	(B-1558)	(B-1558)	(B-1556)	(B-1556)	(B-1556)	(B-1556)	

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				ABS					
				High toughness					
				High toughness ↔ High stiffness			Painting		
Properties (under ISO 10350)	Standard	Conditions	Units	IM30	IM20	IM15	IM10	ID31J	ID510
1. Rheological properties									
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	4	6	7	8	19	18
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	4	7	8	8	20	19
2. Mechanical properties									
Tensile stress at yield	ISO527-1	50mm/min	MPa	38	44	50	52	42	48
Tensile stress at yield	ISO527-1	5mm/min	MPa	—	—	—	—	—	—
Flexural modulus	ISO178	2mm/min	MPa	1850	2150	2500	2600	2150	2400
Flexural strength	ISO178	2mm/min	MPa	59	66	80	83	67	76
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	42	38	33	29	32	18
	ISO179	0°C	kJ/m²	—	—	—	—	—	—
	ISO179	-30°C	kJ/m²	—	—	—	—	—	—
3. Thermal properties									
Vicat softening temperature	ISO306	Load:50N	°C	97	101	105	106	99	105
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	80	80	84	85	79	84
4. Other properties									
Density	ISO1183	23°C	g/cm³	1.03	1.05	1.05	1.06	1.05	1.05
Rockwell hardness	ISO2039-2	R scale	—	—	—	—	—	—	—
	ISO2039-2	M scale	—	—	—	—	—	—	—
5. Properties under other standards									
Rockwell hardness(2.5mm)	ordinal	R scale	—	87	100	104	106	97	104
Linear expansion coefficient	ASTM D696	—	10⁻⁵/°C	—	—	—	—	—	—
Mold shrinkage	ASTM D955	—	%	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6
Surface resistance	ASTM D257	—	Ω	—	—	—	—	—	—
Volume resistance	original	—	Ω · cm	—	—	—	—	—	—
Thermal conductivity	ASTM D 177	—	W/m·°C	—	—	—	—	—	—
UL class	UL94	—	—	1.5mm HB	1.5mm HB	1.5mm HB	1.5mm HB	—	—
Relative temperature index	UL746A	—	°C	60	60	60	60	—	—
Ball pressure temperature (Registered number)	EMAC	—	°C	90 (B-1558)	95 (B-1560)	95 (B-0634)	95 (B-1560)	—	—

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				ABS			
				Heat resistant			
				high	Extra high	Max.	Hith flow
Properties (under ISO 10350)	Standard	Conditions	Units	181	183	185	A3921
1. Rheological properties							
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	8	5	2	10
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	9	5	2	11
2. Mechanical properties							
Tensile stress at yield	ISO527-1	50mm/min	MPa	45	45	45	52
Tensile stress at yield	ISO527-1	5mm/min	MPa	—	—	—	—
Flexural modulus	ISO178	2mm/min	MPa	2350	2350	2300	2750
Flexural strength	ISO178	2mm/min	MPa	74	75	76	82
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	22	19	15	9
	ISO179	0°C	kJ/m²	—	—	—	—
	ISO179	-30°C	kJ/m²	—	—	—	—
3. Thermal properties							
Vicat softening temperature	ISO306	Load:50N	°C	108	114	124	113
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	88	93	102	94
4. Other properties							
Density	ISO1183	23°C	g/cm³	1.05	1.06	1.07	1.07
Rockwell hardness	ISO2039-2	R scale	—	—	—	—	—
	ISO2039-2	M scale	—	—	—	—	—
5. Properties under other standards							
Rockwell hardness(2.5mm)	ordinal	R scale	—	103	104	103	110
Linear expansion coefficient	ASTM D696	—	10⁻⁵/°C	—	—	—	—
Mold shrinkage	ASTM D955	—	%	0.5–0.7	0.5–0.7	0.5–0.7	0.5–0.7
Surface resistance	ASTM D257	—	Ω	—	—	—	—
Volume resistance	original	—	Ω · cm	—	—	—	—
Thermal conductivity	ASTM D 177	—	W/m·°C	—	—	—	—
UL class	UL94	—	—	1.5mm HB	1.5mm HB	1.5mm HB	1.5mm HB
Relative temperature index	UL746A	—	°C	60	60	60	60
Ball pressure temperature (Registered number)	EMAC	—	°C	100 (B-1564)	105 (B-1534)	120 (B-1536)	105 (B-1534)

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES			ABS		
			GF-reinforced		
				Flame retardant	
Properties (under ISO 10350)	Standard	Conditions	Units	R240A	VGB20
1. Rheological properties					
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	6	17
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	6	16
2. Mechanical properties					
Tensile stress at yield	ISO527-1	50mm/min	MPa	–	
Tensile stress at yield	ISO527-1	5mm/min	MPa	105	78
Flexural modulus	ISO178	2mm/min	MPa	6600	5200
Flexural strength	ISO178	2mm/min	MPa	161	115
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	11	7
	ISO179	0°C	kJ/m²	–	–
	ISO179	-30°C	kJ/m²	–	–
3. Thermal properties					
Vicat softening temperature	ISO306	Load:50N	°C	–	–
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	104	83
4. Other properties					
Density	ISO1183	23°C	g/cm³	1.19	1.32
Rockwell hardness	ISO2039-2	R scale	–	–	–
	ISO2039-2	M scale	–	–	–
5. Properties under other standards					
Rockwell hardness(2.5mm)	ordinal	R scale	–	–	–
Linear expansion coefficient	ASTM D696	–	10⁻⁵/°C	3.3	3.3
Mold shrinkage	ASTM D955	–	%	0.2–0.35	0.3–0.4
Surface resistance	ASTM D257	–	Ω	–	–
Volume resistance	original	–	Ω · cm	–	–
Thermal conductivity	ASTM D 177	–	W/m·°C	–	–
UL class	UL94	–	–	1.5mm HB	1.5mm HB
Relative temperature index	UL746A	–	°C	60	60
Ball pressure temperature (Registered number)	EMAC	–	°C	100 (B-1561)	–

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				ABS				
				Extrusion				
				Extrusion	High molding			Blow
Properties (under ISO 10350)	Standard	Conditions	Units	A4130	AE510	AE490	AE850	IB330
1. Rheological properties								
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	7	8	7	10	1
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	7	8	7	11	2
2. Mechanical properties								
Tensile stress at yield	ISO527-1	50mm/min	MPa	47	39	47	29	44
Tensile stress at yield	ISO527-1	5mm/min	MPa	-	-	-	-	-
Flexural modulus	ISO178	2mm/min	MPa	2450	2750	3950	1450	2450
Flexural strength	ISO178	2mm/min	MPa	77	67	78	47	82
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	27	11	7	35	17
	ISO179	0°C	kJ/m²	-	-	-	-	-
	ISO179	-30°C	kJ/m²	-	-	-	-	-
3. Thermal properties								
Vicat softening temperature	ISO306	Load:50N	°C	102	99	103	89	113
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	82	80	88	74	93
4. Other properties								
Density	ISO1183	23°C	g/cm³	1.05	1.18	1.16	1.01	1.06
Rockwell hardness	ISO2039-2	R scale	-	-	-	-	-	-
	ISO2039-2	M scale	-	-	-	-	-	-
5. Properties under other standards								
Rockwell hardness(2.5mm)	ordinal	R scale	-	102	-	-	68	106
Linear expansion coefficient	ASTM D696	-	10⁻⁵/°C	7-9	6-7	4-5	-	-
Mold shrinkage	ASTM D955	-	%	0.4-0.6	0.4-0.6	0.4-0.6	-	0.5-0.7
Surface resistance	ASTM D257	-	Ω	-	-	-	-	-
Volume resistance	original	-	Ω · cm	-	-	-	-	-
Thermal conductivity	ASTM D 177	-	W/m·°C	-	-	-	-	-
UL class	UL94	-	-	-	-	-	-	-
Relative temperature index	UL746A	-	°C	-	-	-	-	-
Ball pressure temperature (Registered number)	EMAC	-	°C	-	-	-	-	-

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				ABS			
				Long lasting antistatic/Electrically conductive			
				Long lasting antistatic		Electrically conductive	
Properties (under ISO 10350)	Standard	Conditions	Units	A100	IC39A	IC10N	IC24
1. Rheological properties							
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	37	84	2	12
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	38	73	1	11
2. Mechanical properties							
Tensile stress at yield	ISO527-1	50mm/min	MPa	44	54	–	79
Tensile stress at yield	ISO527-1	5mm/min	MPa	–	–	133	–
Flexural modulus	ISO178	2mm/min	MPa	2100	2450	10000	2800
Flexural strength	ISO178	2mm/min	MPa	68	78	186	114
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	21	2	8	6
	ISO179	0°C	kJ/m²	–	–	–	–
	ISO179	-30°C	kJ/m²	–	–	–	–
3. Thermal properties							
Vicat softening temperature	ISO306	Load:50N	°C	92	98	110	106
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	75	81	100	101
4. Other properties							
Density	ISO1183	23°C	g/cm³	1.07	1.09	1.12	1.08
Rockwell hardness	ISO2039-2	R scale	–	–	–	–	–
	ISO2039-2	M scale	–	–	–	–	–
5. Properties under other standards							
Rockwell hardness(2.5mm)	ordinal	R scale	–	94	98	–	–
Linear expansion coefficient	ASTM D696	–	10⁻⁵/°C	–	–	–	–
Mold shrinkage	ASTM D955	–	%	–	–	0.1-0.2	0.2-0.3
Surface resistance	ASTM D257	–	Ω	–	–	4	E+4
Volume resistance	original	–	Ω · cm	–	–	5 × 10⁻¹	E+3
Thermal conductivity	ASTM D 177	–	W/m·°C	–	–	0.26	–
UL class	UL94	–	–	–	–	1.5mm HB	1.5mm HB
Relative temperature index	UL746A	–	°C	–	–	60	–
Ball pressure temperature (Registered number)	EMAC	–	°C	–	–	–	–

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				ABS		
				Chemical resistance		
				Super \longleftrightarrow general		
Properties (under ISO 10350)	Standard	Conditions	Units	IX700	IX600	IX220
1. Rheological properties						
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	6	7	15
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	6	7	16
2. Mechanical properties						
Tensile stress at yield	ISO527-1	50mm/min	MPa	41	40	48
Tensile stress at yield	ISO527-1	5mm/min	MPa	—	—	—
Flexural modulus	ISO178	2mm/min	MPa	1900	1900	2350
Flexural strength	ISO178	2mm/min	MPa	66	56	74
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	34	40	36
	ISO179	0°C	kJ/m²	—	—	—
	ISO179	-30°C	kJ/m²	—	—	—
3. Thermal properties						
Vicat softening temperature	ISO306	Load:50N	°C	97	96	99
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	80	80	80
4. Other properties						
Density	ISO1183	23°C	g/cm³	1.06	1.06	1.05
Rockwell hardness	ISO2039-2	R scale	—	—	—	—
	ISO2039-2	M scale	—	—	—	—
5. Properties under other standards						
Rockwell hardness(2.5mm)	ordinal	R scale	—	91	94	103
Linear expansion coefficient	ASTM D696	—	10⁻⁵/°C	—	—	—
Mold shrinkage	ASTM D955	—	%	0.4–0.6	0.4–0.6	0.4–0.6
Surface resistance	ASTM D257	—	Ω	—	—	—
Volume resistance	original	—	Ω · cm	—	—	—
Thermal conductivity	ASTM D 177	—	W/m·°C	—	—	—
UL class	UL94	—	—	—	—	—
Relative temperature index	UL746A	—	°C	—	—	—
Ball pressure temperature (Registered number)	EMAC	—	°C	90 (B-2428)	—	95 (B-2464)

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				ABS	
				High light resistance	
Properties (under ISO 10350)	Standard	Conditions	Units	FW130	FW920
1. Rheological properties					
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	25	30
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	26	-
2. Mechanical properties					
Tensile stress at yield	ISO527-1	50mm/min	MPa	43	38
Tensile stress at yield	ISO527-1	5mm/min	MPa	-	-
Flexural modulus	ISO178	2mm/min	MPa	2000	2000
Flexural strength	ISO178	2mm/min	MPa	65	58
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	18	18
	ISO179	0°C	kJ/m²	-	-
	ISO179	-30°C	kJ/m²	-	-
3. Thermal properties					
Vicat softening temperature	ISO306	Load:50N	°C	90	86
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	73	73
4. Other properties					
Density	ISO1183	23°C	g/cm³	1.06	-
Rockwell hardness	ISO2039-2	R scale	-	-	-
	ISO2039-2	M scale	-	-	-
5. Properties under other standards					
Rockwell hardness(2.5mm)	ordinal	R scale	-	93	-
Linear expansion coefficient	ASTM D696	-	10⁻⁵/°C	-	-
Mold shrinkage	ASTM D955	-	%	0.4-0.6	-
Surface resistance	ASTM D257	-	Ω	-	-
Volume resistance	original	-	Ω · cm	-	-
Thermal conductivity	ASTM D 177	-	W/m·°C	-	-
UL class	UL94	-	-	-	-
Relative temperature index	UL746A	-	°C	-	-
Ball pressure temperature (Registered number)	EMAC	-	°C	-	-

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				ABS		
				Flame Retardant		
				Halogen	Non-halogen	
Properties (under ISO 10350)	Standard	Conditions	Units	VA58	VA518	VN33H
1. Rheological properties						
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	25	58	81
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	25	58	80
2. Mechanical properties						
Tensile stress at yield	ISO527-1	50mm/min	MPa	47	42	50
Tensile stress at yield	ISO527-1	5mm/min	MPa	—	—	—
Flexural modulus	ISO178	2mm/min	MPa	2550	2400	2800
Flexural strength	ISO178	2mm/min	MPa	79	71	81
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	11	9	14
	ISO179	0°C	kJ/m²	—	—	—
	ISO179	-30°C	kJ/m²	—	—	—
3. Thermal properties						
Vicat softening temperature	ISO306	Load:50N	°C	92	90	87
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	76	74	70
4. Other properties						
Density	ISO1183	23°C	g/cm³	1.20	1.19	1.07
Rockwell hardness	ISO2039-2	R scale	—	—	—	—
	ISO2039-2	M scale	—	—	—	—
5. Properties under other standards						
Rockwell hardness(2.5mm)	ordinal	R scale	—	—	—	—
Linear expansion coefficient	ASTM D696	—	10⁻⁵ / °C	—	—	—
Mold shrinkage	ASTM D955	—	%	0.4–0.6	0.4–0.6	0.4–0.6
Surface resistance	ASTM D257	—	Ω	—	—	—
Volume resistance	original	—	Ω · cm	—	—	—
Thermal conductivity	ASTM D 177	—	W/m·°C	—	—	—
UL class	UL94	—	—	2.1mm V-0 2.5mm 5VA	1.5mm V-0 2.0mm 5VA	1.6mm V-2 3.2mm V-2
Relative temperature index	UL746A	—	°C	60	60	60
Ball pressure temperature (Registered number)	EMAC	—	°C	80 (B-2285)	—	85 (B-2411)

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				AS						
				General purpose						
				General			Heat resistant		High clarity	
Properties (under ISO 10350)	Standard	Conditions	Units	767	T8701	769	789	783	T8707	CS747
1. Rheological properties										
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	12	23	30	27	9	30	12
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	13	25	31	29	10	32	13
2. Mechanical properties										
Tensile stress at yield	ISO527-1	50mm/min	MPa	–	–	–	–	–	–	–
Tensile stress at yield	ISO527-1	5mm/min	MPa	70	68	64	72	74	61	68
Flexural modulus	ISO178	2mm/min	MPa	3700	3650	3700	3800	3750	3650	3700
Flexural strength	ISO178	2mm/min	MPa	130	125	123	138	139	120	124
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	1.3	1.3	1.2	1.3	1.3	1.2	1.3
	ISO179	0°C	kJ/m²	–	–	–	–	–	–	–
	ISO179	-30°C	kJ/m²	–	–	–	–	–	–	–
3. Thermal properties										
Vicat softening temperature	ISO306	Load:50N	°C	103	102	102	104	105	101	102
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	88	87	87	89	89	86	86
4. Other properties										
Density	ISO1183	23°C	g/cm³	1.07	1.07	1.07	1.08	1.08	1.07	1.07
Rockwell hardness	ISO2039-2	R scale	–	–	–	–	–	–	–	–
	ISO2039-2	M scale	–	–	–	–	–	–	–	–
5. Properties under other standards										
Rockwell hardness(2.5mm)	ordinal	R scale	–	–	–	–	–	–	–	–
Linear expansion coefficient	ASTM D696	–	10⁻⁵/°C	–	–	–	–	–	–	2.8
Mold shrinkage	ASTM D955	–	%	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	0.4–0.6	0.15–0.35
Surface resistance	ASTM D257	–	Ω	–	–	–	–	–	–	–
Volume resistance	original	–	Ω · cm	–	–	–	–	–	–	–
Thermal conductivity	ASTM D 177	–	W/m·°C	–	–	–	–	–	–	–
UL class	UL94	–	–	1.5mm HB	–	1.5mm HB	1.5mm HB	1.5mm HB	1.5mm HB	1.5mm HB
Relative temperature index	UL746A	–	°C	50	–	50	50	50	50	50
Ball pressure temperature (Registered number)	EMAC	–	°C	95 (B-1573)	–	95 (B-1573)	95 (B-1573)	95 (B-1573)	–	100 (B-1574)

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				AS GF	
Properties (under ISO 10350)	Standard	Conditions	Units	R340T	R440T
1. Rheological properties					
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	5	11
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	4	10
2. Mechanical properties					
Tensile stress at yield	ISO527-1	50mm/min	MPa	-	-
Tensile stress at yield	ISO527-1	5mm/min	MPa	125	114
Flexural modulus	ISO178	2mm/min	MPa	8000	7950
Flexural strength	ISO178	2mm/min	MPa	184	170
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	5	5
	ISO179	0°C	kJ/m²	-	-
	ISO179	-30°C	kJ/m²	-	-
3. Thermal properties					
Vicat softening temperature	ISO306	Load:50N	°C	-	-
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	107	109
4. Other properties					
Density	ISO1183	23°C	g/cm³	1.21	1.22
Rockwell hardness	ISO2039-2	R scale	-	-	-
	ISO2039-2	M scale	-	-	-
5. Properties under other standards					
Rockwell hardness(2.5mm)	ordinal	R scale	-	-	-
Linear expansion coefficient	ASTM D696	-	10⁻⁵/°C	2.8	2.8
Mold shrinkage	ASTM D955	-	%	0.15–0.35	0.15–0.35
Surface resistance	ASTM D257	-	Ω	-	-
Volume resistance	original	-	Ω · cm	-	-
Thermal conductivity	ASTM D 177	-	W/m·°C	-	-
UL class	UL94	-	-	1.5mm HB	1.5mm HB
Relative temperature index	UL746A	-	°C	50	50
Ball pressure temperature (Registered number)	EMAC	-	°C	100 (B-1574)	100 (B-1574)

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				ACS
				Flame retardant
				Halogen
Properties (under ISO 10350)	Standard	Conditions	Units	NF920
1. Rheological properties				
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	59
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	55
2. Mechanical properties				
Tensile stress at yield	ISO527-1	50mm/min	MPa	44
Tensile stress at yield	ISO527-1	5mm/min	MPa	–
Flexural modulus	ISO178	2mm/min	MPa	2550
Flexural strength	ISO178	2mm/min	MPa	70
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	7
	ISO179	0°C	kJ/m²	–
	ISO179	-30°C	kJ/m²	–
3. Thermal properties				
Vicat softening temperature	ISO306	Load:50N	°C	88
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	74
4. Other properties				
Density	ISO1183	23°C	g/cm³	1.16
Rockwell hardness	ISO2039-2	R scale	–	101
	ISO2039-2	M scale	–	–
5. Properties under other standards				
Rockwell hardness(2.5mm)	ordinal	R scale	–	–
Linear expansion coefficient	ASTM D696	–	10⁻⁵/°C	7-10
Mold shrinkage	ASTM D955	–	%	0.4-0.7
Surface resistance	ASTM D257	–	Ω	–
Volume resistance	original	–	Ω · cm	–
Thermal conductivity	ASTM D 177	–	W/m·°C	–
UL class	UL94	–	–	2.5mm 5VA 1.5mm V-0
Relative temperature index	UL746A	–	°C	50
Ball pressure temperature (Registered number)	EMAC	–	°C	80
				–

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.

BASIC PROPERTIES				Alloy			
				Painting / Paintless			
				Painting & Low linear expansion coefficient	Good surface appearance unpainted		
Properties (under ISO 10350)	Standard	Conditions	Units	E710T	AT11N	AT27	AT900
1. Rheological properties							
Melt mass-flow rate	ISO1133	220°C, 98N	g/10min	–	16	14	12
Melt volume-flow rate	ISO1133	220°C, 98N	cm³/10min	15(*)	17	14	13
2. Mechanical properties							
Tensile stress at yield	ISO527-1	50mm/min	MPa	43	–	60	64
Tensile stress at yield	ISO527-1	5mm/min	MPa	–	77	–	–
Flexural modulus	ISO178	2mm/min	MPa	3400	3600	2900	2950
Flexural strength	ISO178	2mm/min	MPa	70	122	95	99
Charpy impact strength(notched)	ISO179	23°C	kJ/m²	6	1	6	3
	ISO179	0°C	kJ/m²	–	–	–	–
	ISO179	-30°C	kJ/m²	–	–	–	–
3. Thermal properties							
Vicat softening temperature	ISO306	Load:50N	°C	103	98	104	104
Deflection temperature under load	ISO75-1,2	1.8MPa	°C	84	79	82	81
4. Other properties							
Density	ISO1183	23°C	g/cm³	1.20	1.12	1.11	1.14
Rockwell hardness	ISO2039-2	R scale	–	–	–	–	–
	ISO2039-2	M scale	–	–	–	–	–
5. Properties under other standards							
Rockwell hardness(2.5mm)	ordinal	R scale	–	–	122	117	118
Linear expansion coefficient	ASTM D696	–	10⁻⁵/°C	6–8	–	–	–
Mold shrinkage	ASTM D955	–	%	0.4–0.6	–	–	–
Surface resistance	ASTM D257	–	Ω	–	–	–	–
Volume resistance	original	–	Ω · cm	–	–	–	–
Thermal conductivity	ASTM D 177	–	W/m·°C	–	–	–	–
UL class	UL94	–	–	–	–	–	–
Relative temperature index	UL746A	–	°C	–	–	–	–
Ball pressure temperature (Registered number)	EMAC	–	°C	–	–	–	–

(*) Conditions : 240°C, 49N

All values are presented as typical results obtained by the indicated test methods, presented only as a basic guide to grade selection and not as any warranty or specification, and are subject to change without notice.